Product Data Sheet

2-tonne bulk bag · Test results

In stock now in 2-tonne bulk bags.

Key results

2 MT	26.0 MPa	47.4-48.0	135 min
Per bulk bag	or more, 3-day strength	MPa, 28-day strength	Initial set from

Test results

Test	Result	Status
3-day compressive strength	26.0 to 28.1 MPa	
28-day compressive strength	47.4 to 48.0 MPa	
Initial setting time	135 to 150 min	
Final setting time	165 to 180 min	
Normal consistency	27%	
Fineness	491 m²/kg	**Satisfactory**
Density	3.01 g/cm³	**Satisfactory**
Flow	112.0%	**Satisfactory**
Autoclave expansion	0.01%	**Satisfactory**

Results apply to the 2-tonne bulk bag. Test documents available on request.

Why it matters on site

Strong early strength at 3 days, steady gain to 28 days, and consistent results across tests.

Order: rhcone.com/order · **Calls and WhatsApp:** (876) 443-7598

Packaging and Ordering

2-tonne bulk bags

Order online or by call or WhatsApp.

Pack size

2-tonne bulk bag

- 2 MT per bulk bag
- In stock now
- Tested, see page 1
- Suits block makers, batching and large pours
- Lift with suitable equipment only

Supply

Supplied from	Port Esquivel, St Catherine, Jamaica

Storage and handling

Keep bags dry, off the ground and under cover.

Wear gloves and eye protection when handling cement.

Avoid breathing dust. Wash skin that comes into contact with wet cement.

Use stock in order of delivery.

Order

Order online: https://rhcone.com/order
Calls and WhatsApp: (876) 443-7598
Location: Port Esquivel, St Catherine